



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Understanding the sub-T_g relaxation in mechanically excited chalcogenide glasses by comparison with hyperquenched glasses

Yue, Yuanzheng; Qiao, Ang; Tao, Haizheng

Publication date:
2017

Document Version
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Yue, Y., Qiao, A., & Tao, H. (2017). *Understanding the sub-T_g relaxation in mechanically excited chalcogenide glasses by comparison with hyperquenched glasses*. Abstract from 12th Pacific Rim Conference on Ceramic and Glass Technology including Glass & Optical Materials Division Meeting 2017, Waikoloa, Hawaii, United States.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Understanding the sub- T_g relaxation in mechanically excited chalcogenide glasses by comparison with hyperquenched glasses

Yuanzheng Yue^{1,2*}, Ang Qiao¹, Haizheng Tao¹

¹ *State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan 430070, China*

² *Department of Chemistry and Bioscience, Aalborg University, DK-9220 Aalborg, Denmark*

*Corresponding author. E-mail: yy@bio.aau.dk

We investigate the sub- T_g enthalpy relaxation in a milling derived, i.e., mechanically excited (ME) chalcogenide glass (Ag_3PS_4 glass) by comparing with the hyperquenched (HQ) ($>10^5$ K/s) oxide and metallic glasses. This has been done using differential scanning calorimetry (DSC). We have found that two distinct, but also correlated peaks of sub- T_g energy release with similar intensity occur in the ME glass during DSC upscanning. Such relaxation pattern is in strong contrast to the asymmetric peak observed in the HQ oxide and metallic glasses. The low-temperature relaxation peak of the ME glass is attributed to β -relaxation. β -relaxation originates from the local motion of mobile silver ions from unstable to relatively stable sites. The high-temperature peak is a result of the α -relaxation associated with the recovery of the distorted covalently bonded PS_4 units. However, for the HQ glasses, the low-temperature peak is manifested as a shoulder superimposed on the main peak. The HQ glasses lie significantly higher on potential energy landscape than the ME glass. This work implies that the ME glass is of higher structural heterogeneities than the HQ ones.